

# Technical Data Sheet

B290 Penetrating Threadlock

#### **PRODUCT DESCRIPTION**

B290 Penetrating Threadlock is a very low viscosity, medium to high strength penetrating grade threadlocker that is suitable for preassembled threads or for post-application. The wicking action ensures holes and porosities in castings and welds can be filled and sealed. Ideal for locking instrumentation fasteners, electrical connectors and set screws.

#### THREADLOCKERS

Bondloc threadlockers are single-component liquids that cure at room temperature to a hard, solid thermoset plastic when applied between steel, aluminium, brass and most other metal surfaces. They cure with the absence of air and when in contact with metal ions, the adhesive completely fills the gaps between mating threads to lock threads and joints. This prevents unwanted movement, loosening, leaks and corrosion.

#### ANAEROBIC KEY FEATURES

- Single-component clean and easy to apply
- Prevent unwanted loosening, leaks, and corrosion
- Reduces costs over mechanical fittings
- Resists vibration
- Can be used on all sizes of fasteners reduces inventory costs
- Seals threads and increases friction.

#### TEST PERFORMANCE

Full Cure Time	12 hours @ 22°C
Strength – ISO 10964	Unseated
Breakaway	≥12Nm
Prevailing	≥29Nm
Strength – ISO 10964	Pre – torqued
Breakloose:	30Nm
Prevailing:	40Nm

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

### TEST CRITERIA

The test performance data reported was measured according to ISO 10964 using M10 mild steel bolts and cured 24 hours at 22°C (71.6°F) before testing

#### **TECHNICAL FEATURES**

Base technology	Acrylic
Colour	Green (UV Positive)
Cure	Anaerobic
Viscosity Brookfield Sp1 @50rpm@25°C	20-55 cps
Cure speed without Activator	7 minutes @ 22°C
Max Thread Size	M2-M12
Shelf Life	24 months @ 22°C
Specific Gravity ASTM D1475-13 (2020)	1.08
Temperature Range	-55°C to +150°C

#### INSTRUCTIONS FOR USE

Clean surfaces to be bonded with B7063 Solvent Cleaner and allow to dry

Apply adhesive to the threads, apply sufficient adhesive to fill the voids and then assemble and tighten as required

When the cure speed is slow use B7649 Anaerobic activator for increased cure and set times.

#### LIMITATIONS

 This product is not recommended for use in pure oxygen and/or oxygen-rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. Material removed from containers may be contaminated during use. Do not return product to the



+44 (0) 1299 269 269 sales@bondloc.co.uk



## **Technical Data Sheet** B290 Penetrating Threadlock

original container. Bondloc UK Ltd will not assume responsibility for product that has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact our office, and report the problem

• Anaerobic products are not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

#### STORAGE

Store product in the unopened container in a dry area out of direct sunlight. Storage below 7°C or greater than 28°C can adversely affect product performance. If stored properly, this product has a shelf life of 24 months.

#### HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

#### PACKAGING FORMAT

Bottles.....10ml, 25ml, 50ml, 250ml

#### PRODUCT DISCLAIMER

Bondloc offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bondloc's research only. Since the conditions and methods of use of the products are beyond our control, Bondloc expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BONDLOC'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for the application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. Bondloc does not augrantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS.

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk

