



# Technical Data Sheet

## WL77 Pipeséal

September 2023

### PRODUCT DESCRIPTION

WL77 Pipeséal is a medium-strength anaerobic thread sealant formulated with Teflon designed for the locking and sealing of metal pipes and fittings. It provides an instant low-pressure seal, does not shrink or creep and seals all types of threaded connections. Excellent chemical and solvent resistance to ethanol, motor oil, unleaded petrol, acetone, and brake fluid. Ideal for large fittings, sprinklers system, water, and gas line fittings.

WL77 is part of the Bondloc "Safer Product" range of anaerobic adhesives. The range provides excellent and proven performance with no safety or risk phrases and no hazardous pictograms on the product label.

### THREAD SEALANTS

Bondloc Thread Sealants are single-component liquids that cure at room temperature in the absence of air and when in contact with metal ions. The adhesive completely fills the gaps between mating threads to lock threads and joints. Bondloc Thread Sealants replace conventional methods used such as PTFE tape, O-ring, hemp etc which can all cause issues.

### ANAEROBIC KEY FEATURES

- Single-component – clean and easy to apply
- Do not creep, shrink or block systems
- Can be used on any size of pipe fitting
- Replace all types of tape and paste sealants
- The seal resists vibration and shock loads
- Protect mated threaded areas against corrosion and galling.

### TECHNICAL FEATURES

Base technology	Dimethacrylate ester
Colour	Yellow (UV Positive)
Cure	Anaerobic
Viscosity Brookfield Sp7@20rpm@25°C	100,000 – 200,000 cps
Cure Time (Full)	24 hours @ 23°C
Cure Time (Initial)	30 mins @ 23°C
Gap Fill	>0.20mm
Shelf Life	24 months @ 22°C
Specific Gravity ASTM D1475-13 (2020)	1.10
Temperature Range	-55°C to +180°C

### TEST PERFORMANCE

Full Cure Time	24 hours @ 23°C
Strength – ISO 10964 Breakaway Prevailing	Unseated ≥15Nm ≥5Nm
Shear Strength – ISO 4587	5-15N/mm <sup>2</sup>

### TEST CRITERIA

The test performance data reported was measured according to ISO 10964 using M10 black oxide bolts and mild steel nuts, cured 24 hours at 22°C (71.6°F) before testing.

### INSTRUCTIONS FOR USE

- Clean surfaces to be bonded with B7063 Solvent Cleaner and allow to dry
- Apply adhesive to the surface and assemble parts
- When the cure speed is slow use B7649 Anaerobic activator for increased cure and set times.

Bondloc UK Ltd.  
Units 1 & 2  
Bewdley Business Park  
Bewdley, Worcestershire  
DY12 2TZ, UK

+44 (0) 1299 269 269  
sales@bondloc.co.uk





# Technical Data Sheet

## WL77 Pipeseal

September 2023

### LIMITATIONS

- This product is not recommended for use in pure oxygen and/or oxygen-rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. Material removed from containers may be contaminated during use. Do not return the product to the original container. Bondloc UK Ltd will not assume responsibility for product that has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact our office, and report the problem
- Anaerobic products are not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

### STORAGE

Store product in the unopened container in a dry area out of direct sunlight. Storage below 7°C or greater than 28°C can adversely affect product performance. If stored properly, this product has a shelf life of 24 months.

### HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

### PACKAGING FORMAT

Bottles.....50ml, 250ml

### PRODUCT DISCLAIMER

Bondloc offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bondloc's research only. Since the conditions and methods of use of the products are beyond our control, Bondloc expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BONDLOC'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for the application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. Bondloc does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS.

Bondloc UK Ltd.  
Units 1 & 2  
Bewdley Business Park  
Bewdley, Worcestershire  
DY12 2TZ, UK

+44 (0) 1299 269 269  
sales@bondloc.co.uk

