

Technical Data Sheet

Bondloc B495 General Purpose

PRODUCT DESCRIPTION

B495 is a general purpose cyanoacrylate instant adhesive.

APPLICATIONS

B495 bonds metals, plastics, wood, ceramics, rubber, leather, card, glass and many other materials.

INSTRUCTIONS FOR USE

Clean and dry surfaces to be bonded. Apply adhesive sparingly to one surface and assemble parts. Hold or clamp parts together for 60 seconds. Leave for 1 hour to fully cure. Activators and primers may be used to aid bonding.

LIQUID PROPERTIES

Ester base	Ethyl cyanoacrylate
Appearance	Clear Liquid
Specific Gravity 25°C	1.043g/cm³
Shelf life	12 months unopened
Viscosity Brookfield - S p 1 @20rpm @25°C	45 - 65 cps

STORAGE

Bondloc cyanoacrylates should ideally be stored in original sealed containers until used. Containers should be stored between 2°C and 10°C with a maximum storage temperature of 25°C. Avoid exposure to strong light and heat sources. Refrigeration can prolong shelf life.

TEMPERATURE RESISTANCE

Tested on mild steel cured for 24 hours, conditioned to test temperature for 1 hour before pull-test.

ENVIRO-CHEMICAL RESISTANCE

Exposed to conditions for 1000 hours at 22°C except for 98% RH which had an exposure of 42°C.

CURED PERFORMANCE

Cured Speed

Defined as the time taken to develop a strength of 0.1N/mm² at 22°C and 50% relative humidity.

∽.	2 Control of 22 Control of Contro		
	Balsa	<5 seconds	
	Nitrile	<5 seconds	
	Neoprene	<5 seconds	
	EPDM	<5 seconds	
	Mild steel (degreased)	5-10 seconds	
	Polycarbonate	10-15 seconds	
	ABS	<5 seconds	

SHEAR STRENGTH

Steel	15-25 N/mm²
Aluminum	7-10 N/mm²
Nitrile Rubber	5-10 N/mm ²
Polycarbonate	5-10 N/mm²
ABS	6-10 N/mm²

TENSILE STRENGTH

Nitrile Rubber	5-15 N/mm²
Neoprene	5-15 N/mm²
EPDM	2-6 N/mm²

HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

PACKAGING FORMAT

Bottles.....20g, 50g, 500g Clam Packs.....20g

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk



Revision date: 28/09/2023 Revision: 2 Supersedes date: 13/11/2017



Technical Data Sheet

Bondloc B495 General Purpose

PRODUCT DISCLAIMER

Bondloc offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bondloc's research only. Since the conditions and methods of use of the products are beyond our control, Bondloc expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BONDLOC'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for the application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. Bondloc does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS.

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk

