

Technical Data Sheet

Bondloc BACT Cyanoacrylate Activator

PRODUCT DESCRIPTION

Bondloc Activator is a low viscosity, solvent based cyanoacrylate adhesive activator which contains active components dissolved in a hydrocarbon solvent.

APPLICATIONS

Bondloc Activator is used to reduce fixing times and ensure that excess adhesive is fully cured. Bondloc activator also reduces blooming and odour. It is particularly useful for production lines such as electronics assembly and UPVC window trim bonding.

USEFUL NOTES

- Reduces blooming
- Reduces odour
- Fast acting
- Easy to use

INSTRUCTIONS FOR USE

Spray a small quantity of Bondloc Activator on to one substrate only. Allow solvent to evaporate. Apply cyanoacrylate adhesive to the other substrate and bring together curing will occur almost instantly. Take precautions not to spray Bondloc activator near unused cyanoacrylate adhesive as this will cure off.

STORAGE

Bondloc Activator will have a 12 month minimum shelf life if stored between 5°C and 25°C.

CHARACTERISTICS

Chemical base	Hydrocarbon solvent
Appearance	Colourless
Viscosity	1 mPas @ 20°C
Flash point	0°C
Density	0.79 g/ml
Aerosol Propellant	co2

HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

PACKAGING FORMAT

Aerosol......200ml, 400ml

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.



Technical Data Sheet

Bondloc BCA MV Superglue

PRODUCT DESCRIPTION

BCA MV Superglue bonds metals, plastics, wood, ceramics, rubber, leather, card, glass and many other materials.

INSTRUCTIONS FOR USE

Clean and dry surfaces to be bonded. Apply adhesive sparingly to one surface and assemble parts. Hold or clamp parts together for 60 seconds. Leave for 1 hour to fully cure. Activators and primers may be used to aid bonding.

LIQUID PROPERTIES

Ester base	Ethyl cyanoacrylate
Appearance	Clear, colourless
Specific Gravity 25°C	1.06 g/cm2
Shelf life	12 months unopened
Viscosity @ 25°C	90 – 120cps
Flash Point	85°C

CURED PERFORMANCE

Cured speed – defined as the time taken to develop a strength of 0.1N/mm² at 22°C and 50% relative humidity

strength of 0.114/11111 at 22 C and 30% relative numbers.		
Balsa	<3 seconds	
Nitrile	<5seconds	
Neoprene	<5 seconds	
EPDM	<5 seconds	
Steel	25-40 seconds	
Polycarbonate	10-30 seconds	
ABS	10-15 seconds	

STORAGE

BCA MV should ideally be stored in original sealed containers until used. Containers should be stored between 2°C and 10°C with a maximum storage temperature of 25°C. Avoid exposure to strong light and heat sources. Refrigeration can prolong shelf life.

SHEAR STRENGTH

Steel	25 N/mm²
Aluminium	7-10 N/mm²
Nitrile Rubber	5-10 N/mm²
Polycarbonate	5-10 N/mm²
ABS	6-10 N/mm²

TENSILE STRENGTH


Nitrile Rubber	5-15 N/mm²
Neoprene	5-15 N/mm ²
EPDM	2-6 N/mm²

TEMPERATURE RESISTANCE

Tested on mild steel cured for 24 hours, conditioned to test temperature for 1 hour before pull-test.

ENVIRO-CHEMICAL RESISTANCE

Exposed to conditions for 1000 hours at 22°C except for 98% RH which had an exposure of 42°C.



HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

PACKAGING FORMAT

Bottles......10g, 20g, 50g, 500g

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.