

# **Technical Data Sheet** B2060 60 Second Epoxy Resin

#### **PRODUCT DESCRIPTION**

B2060 is a two part rapid cold curing epoxy adhesive. It bonds a variety of substrates including steel, aluminium, composites, ceramics and rigid plastics.

# **APPLICATIONS**

B2060 I suitable for bonding a wide range of surfaces including steel, aluminium, and galvanized iron. It reacts within a minute to give a tough resilient bond on a wide variety of surfaces.

# **USEFUL HINTS/NOTES**

- Clean & easy to use.
- Viscous but not thixotropic.
- Rapid Curing.

# **INSTRUCTIONS FOR USE**

Proper surface preparation is essential to the success of any epoxy application. In all cases the surface should be clean, dry free from any oils and rough.

- Remove all oils, dirt and grease by means of a strong cleaner/degreaser.
- Mix equal quantities of the two parts and stir thoroughly until a uniformed colour is obtained. Where a static mixing nozzle is supplied the 2 parts will be mixed correctly upon dispending.
- Apply to one surface and offer up the second surface. Clamp or jig together under light pressure.
- Leave to cure at room temperature.

## **TECHNICAL FEATURES**

	Part 1	Part 2
Physical form	Viscous Liquid	Viscous Liquid
Chemical Type	Ероху	Mercaptan and Polyamide
Appearance	Clear	Blue
Viscosity @ 25°C	100cps	130cps
Specific Gravity	1.17	1.14
Mix ratio	1:1	
Work Life	As a mix 40-70 seconds	
Temperature Range	-40°C - 121°C	

# **CURED PERFORMANCE**

Plastics	Shear Strength PSI
ABS	210
GRP	540
HIPS	210
Nylon	180
Perspex	330
Upvc	170
Polycarbonate	240
Metals	Shear Strength PSI
Steel	550
Steel, Abraded	900
Stainless Steel	1050
Aluminium	650
Aluminium, Abraded	960
Galvanised Iron	800
Others	
Plywood	680
Tiywood	000

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK







# **Technical Data Sheet** B2060 60 Second Epoxy Resin

#### **HEALTH & SAFETY**

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

#### **STORAGE**

Store product in the unopened container in a dry area out of direct sunlight. Storage between 5°C and 25°C. If stored properly, this product has a shelf life of 12 months.

### **PACKAGING FORMAT**

Cartridge......25ml Clam.....25ml

### PRODUCT DISCLAIMER

Bondloc offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bondloc's research only. Since the conditions and methods of use of the products are beyond our control, Bondloc expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BONDLOC'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for the application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. Bondloc does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS.

Bondloc UK Ltd. Units 1 & 2 Bewdley Business Park Bewdley, Worcestershire DY12 2TZ, UK

+44 (0) 1299 269 269 sales@bondloc.co.uk

